



## Poliolefini, Divisione della F.A.R. S.p.a.

STABILIMENTO: 13100 Verucchio - Via E. Ara, 48 - Tel. 0161-298611 / Fax 0161-391238

DIREZIONE: 20093 Cologno Monzese (MI) - Viale Emilia, 85 - Tel. 02/25191 - Fax 02/251940

### SALES SPECIFICATION

Specification: 01 Revision: 05 Data: 14/07/09

Issued: **R&D**  
(position/signature)

Approved: **CD**  
(position/signature)

Copy to: Sales - Production - Quality Control - Quality Assurance

**PRODUCT: TRIMETHYLOLPROPANE - MOLTEN - FLAKES**

Properties	Unit	Specification limits	Test method	
			Poliolefini	ASTM reference
Purity	%	98,5 min. (1)	009A	-
Hydroxyl number	mg KOH / g	1238 min. (1)	087	E 222
Hydroxyl content	%	37,5 min.	003	E 222
Acidity (as HCOOH)	ppm		086	
Ash content	ppm	50 max.	017	D 482
Moisture on molten	%	0,05 max.	014	E 203
Moisture on flakes (as packed)	%	0,1 max	014	E 203
Solidification point	°C	58 min.	015	D 1493
Colour (on molten)	apha	15 max	019	D 1209

Note: (1) referred to organics, water excluded

Packaging: Kg 25 bags ; big bags, molten

Accettazione della specifica da parte del cliente

Customer

Function

Signature

Date